


TRIBOLOGICAL STUDIES OF DYNAMIC THERMAL SEAL MATERIALS

Jeffrey J. DeMange
Shawn C. Taylor
The University of Toledo



Materials Science & Technology
Thermal Protection Materials and Systems
Salt Lake City, UT
October 24-27, 2016



This research was funded by the U.S. Government under NASA Contract NNC13BA10B. The views and conclusions contained in this document are those of the authors and should not be interpreted as representing the official policies, either expressed or implied, of the U.S. Government.

CONTENTS OF DISCUSSION

- Introduction
 - Description of Dynamic Thermal Barriers
 - Types/Construction of Dynamic Thermal Barriers
- Objectives and Approach
 - Project objectives
 - Tribometer upgrades and checkout
 - Test materials & test parameters
- Tribological Results
 - Previous results from NASP
 - Tribopairs (base materials and coatings)
 - Temperature
 - Load
- Summary, Conclusions, and Challenges

AN INTEGRAL PART OF THE TPS



**Fin Control
Surfaces**

- Referred to as “dynamic thermal seals” or “dynamic seals”
- High-temp. ceramic-based materials
- Installed in TPS interface gaps between moving structures
- Roles
 - Thermal – limit inboard temperatures
 - Structural/physical – survive temps. and wear, not impede actuation/operation of control surface, accommodate deflections



Body Flap



X38 CRV



**Compliant Thermal Barriers
(CTB's)**


DYNAMIC THERMAL SEALS




Compliant Thermal Barrier



Rope Thermal Barrier



Hybrid Sheath Thermal Barrier




Wafer Seals


- Compliant Thermal Barriers (CTB)
 - Nextel™ sheath
 - Saffil® core, spring tube
 - Higher temps, lower stiffness, higher leakage
- Rope Thermal Barriers (RTB)
 - Nextel™ sheath
 - Fiber/fabric/rope core
 - Higher temps, higher stiffness, lower leakage
- Hybrid Sheath Thermal Barriers (HSTB)
 - Metallic wire braid/Nextel™ sheath
 - Saffil®, fiber/fabric/rope core
 - Better wear resistance, lower temps
- Wafer Seals
 - Monolithic materials (metals, ceramics, etc.)
 - Low leakage (tight tolerances)
 - Require preloader

OBJECTIVES

- Overall Objectives
 - Develop a repeatable screening tool to assess tribological performance of dynamic thermal barrier materials
 - Create a database of thermal barrier tribological performance (against TPS or propulsion materials)
 - Improve tribological performance of dynamic thermal barriers
- Dynamic thermal barrier tribological performance
 - Baseline performance against several materials
 - Metal
 - Non-ablative TPS
 - Ablative TPS
 - Effects of various parameters
 - Load
 - Temperature
 - Coatings



HIGH TEMPERATURE TRIBOMETER UPGRADES



HIGH TEMPERATURE TRIBOMETER CHECKOUTS

Test ID	Date	Pin	Plate	Normal Load		Est. CoF, sliding	Published Data	Source
				g	lbf			
0.1	19-Aug	304 SS	304 SS	200	0.39	0.18	---	---
0.2	20-Aug	304 SS	304 SS	200	0.39	0.57	0.53	ASM Handbook ¹
0.3	20-Aug	304 SS	304 SS	400	0.79	0.46	0.53	ASM Handbook ¹
0.4	27-Aug	4130 Steel	4130 Steel	200	0.39	0.42	0.40-0.60	ASM Handbook ² , www.engineersedge.com
0.5	28-Aug	4130 Steel	4130 Steel	400	0.79	0.54	0.40-0.60	ASM Handbook ² , www.engineersedge.com
0.6	28-Aug	4130 Steel	4130 Steel	400	0.79	0.46	0.40-0.60	ASM Handbook ² , www.engineersedge.com
0.7	28-Aug	Teflon	4130 Steel	200	0.39	0.18	0.16	ASM Handbook ³
0.8	28-Aug	Teflon	4130 Steel	400	0.79	0.17	0.16	ASM Handbook ³
0.9	28-Aug	Teflon	Teflon	200	0.39	0.13	0.04-0.07	ASM Handbook
0.10	28-Aug	Teflon	Teflon	200	0.39	0.13	0.04-0.07	ASM Handbook
N0.1	28-Aug	4130 Steel	Nextel 312	100	0.19	0.65	0.50-0.60	NASA TM 105199
N0.2	28-Aug	4130 Steel	Nextel 312	200	0.39	0.60	0.50-0.60	NASA TM 105199

HIGH TEMPERATURE WEAR-RESISTANT COATING CANDIDATES



Coating	Room Temp CoF	High Temp CoF	Max Tested Temp (°C/°F)	Predicted Max Thermal Stability (°C/°F)	Trade Study Weight
NbN/Ag	0.35	0.27	1000/1832	1123/2053	297
Silver Tantalate (AgTaO ₃)	0.60	0.06	750/1382	1172/2142	277
73 TiO ₂ – 27 Cr ₂ O ₃	0.80	0.35	800/1472	1780/3236	272
100 Cr ₂ O ₃	0.25	0.55	800/1472	1650/3002	283
Au/Cr	0.54	0.34	1000/1832	1000/1832	284
MAX phase Ti ₂ AlC	0.70	0.36	550/1022	1400/2552	261
MAX phase Ti ₃ SiC ₂	0.60	0.62	550/1022	1400/2552	249
xo	0.5	0.5	1100	1200	
w	5	9	7	10	

- Challenges with coatings – chemical compatibility/reactions, coating thickness, adherence
- Investigated a nanocomposite MAX phase type coating (SwRI Surface Engineering)

TEST APPROACH

- Test Samples
 - Seal material: Nextel 312 (AF-20) and Nextel 440 (BF-20)
 - 5 harness satin weave
 - Warp: 30 threads per in.; Fill: 26 threads per inch
 - Fabric Coatings: None, TaSiN, TaSiCN (nano-composite coatings)
 - Wear surface: 4130 steel, AETB-8 tile, IN-625
- Test Parameters
 - Load: 2, 8 psi (14, 55 kPa)
 - Temperature: Ambient, 1500°F (Ambient, 815°C)
 - At least 3 tests were conducted for each tribopair at a given test condition

WEAR RESULTS: PREVIOUS TESTING



Dellacorte, C., *et al.* – Studies from 1988-1995



Approach

- Conducted numerous studies
- Pin-on-disk geometry (non-reciprocating)
- “Pin” materials: Nextel 312, Nextel 440, Nextel 550, Nextel 610
- Disk materials: IN 718, IN X-750, Ti₃AlNb
- Temperatures: Ambient - 1832°F (Ambient – 1000°C)
- Loads: 23 - 382 psi (160 - 2633 kPa)
- Coatings: Ag, CaF₂, BN, Au

Results



- CTF generally decreased with increasing temperature (oxide-based fibers)
- CoF's: ~0.6 - 1.0

WEAR RESULTS: EFFECT OF PRELOAD AND CYCLE NUMBER



- CoF lower at higher preload, though likely not statistically significant
- At RT against 4130 steel, low initial CoF, then it increases
- At RT against IN-625, low initial CoF, then it increases
- At 1500°F, CoF was significantly higher starting off and then decreased to fairly high value

WEAR RESULTS: TYPE OF NEXTEL



- Nextel 440 showed slight improvement over Nextel 312
 - Most evident against Shuttle tile
 - Higher CTF likely due to higher breaking strength of N440 (250 lb/in. vs. 150 lbf/in.)
- Shuttle tile exhibited lower CoF than 4130 steel
- CoF appeared to significantly increase for higher temperatures with these tribomaterials

WEAR RESULTS: TYPE OF NEXTEL

Nextel 312


Nextel 440

RT



4130 Steel

Shuttle Tile



4130 Steel

Shuttle Tile

1500°F





Shuttle Tile



Shuttle Tile

WEAR RESULTS: PIN MATERIAL



- Shuttle tile showed some difference when compared to metals
 - Slightly lower CTF
 - Most evident against Shuttle tile
- Shuttle tile exhibited lower CoF than 4130 steel
- CoF appeared to increase significantly with higher temperatures with these tribomaterials


WEAR RESULTS: PIN MATERIAL

4130 Steel


IN 625

Shuttle Tile



RT



1500°F




WEAR RESULTS: EFFECT OF COATINGS



- No significant improvement in CTF with coatings
- Performance comparable (possibly slightly worse) than uncoated Nextel 312
- Possible coating adhesion issues and reactions with Nextel

WEAR RESULTS: EFFECT OF COATINGS


N312




N312 + NTA-3



N312 + NTA-4



RT



1500°F



WEAR RESULTS: EFFECT OF COATINGS

N312



N312 + NTA-5

N312 + NTA-6

RT



1500°F



SUMMARY, CONCLUSIONS, & CHALLENGES

- Rig Upgrade
 - Improved instrumentation, modernized DAQ, augmented stroke length
 - Produced believable, reliable, repeatable results
 - Learned significant lessons to help in design of a newer higher-temperature rig
- Wear Performance of Nextel
 - Nextel durability insufficient for high temperature thermal barrier dynamic operation
 - Significant degradation in wear performance at high temperatures 1500°F
 - Require wear-resistant coatings
 - Initial tests of Nextel against TPS materials demonstrated poor wear resistance, even at room temperature
 - Preliminary tests with Ta-based nano-composite coatings showed no improvement
- Challenges
 - Coatings that are adherent, “non- reactive,” protective, low CoF
 - Coatings appear to work “better” when deposited on opposing wear surface
 - Most studies have deposited on metallic or ceramic substrates
 - Minimal evidence for success depositing on thermal barrier fabric materials

REFERENCES

Blau, P. J. (1992) *Appendix: Static and Kinetic Friction Coefficients for Selected Materials, Friction, Lubrication, and Wear Technology* (Vol 18, pp. 70–75) ASM Handbook, ASM International, 1992.

DellaCorte, C., “Tribological Properties of Alumina-Boria-Silicate Fabric from 25 to 850°C,” NASA TM-100806, March 1988.

DellaCorte, C., “The Experimental Evaluation and Application of High-Temperature Solid Lubricants,” NASA TM-102776, January 1990.

DellaCorte, C. and Steinetz, B., “Relative Sliding Durability of Two Candidate High Temperature Oxide Fiber Seal Materials,” NASA TM-105199, September 1991.

DellaCorte, C. and Steinetz, B., “Tribological Evaluations of an Al_2O_3 - SiO_2 Ceramic Fiber Candidate for High Temperature Sliding Seals,” NASA TM-105611, April 1992.

DellaCorte, C. and Steinetz, B., “Sliding Durability of Candidate Seal Fiber Materials in Hydrogen from 25 to 850°C,” NASA TM-105939, March 1993.

Benoy, P. and DellaCorte, C., “Au/Cr Sputter Coating for the Protection of Alumina During Sliding at High Temperatures,” NASA TM-106853, October, 1995.